

TEST REPORT

APPLICANT : Xindao B.V.

ADDRESS : P.O. Box 3082, 2280 GB, Rijswijk, The Netherlands

SAMPLE DESCRIPTION : Basic two tone backpack

ITEM NO. : P760.02

COUNTRY OF ORIGIN : China

COUNTRY OF DESTINATION : Europe

SAMPLE RECEIVED DATE : 09-Dec-2016

TURN AROUND TIME : 09-Dec-2016 to 19-Dec-2016, 7 Working Days

The following test item(s) was/were performed on selected sample(s) and/or component(s) appointed by applicant.

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Banned AZO Dyes	REACH Annex XVII, Entry 43	Pass
Total Lead Content	REACH Annex XVII, Entry 63	Pass
Polycyclic Aromatic Hydrocarbons (PAHs)	REACH Annex XVII, Entry 50	Pass
Polycyclic Aromatic Hydrocarbons (PAHs)	German GS Specification document: AfPS GS 2014:01 PAK (PAK=PAHs)	Pass

Eurofins (Shanghai) contact information

Customer service: TracyZhang@eurofins.com / 021-61819259

Sales specialist: WandyShen@eurofins.com / 18616155723

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
Eurofins Product Testing Service (Shanghai) Co., Ltd



Joyce Liu
Lab Manager

Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to info.sh@eurofins.com and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to chinacomplaint@eurofins.com and referring to this report number.

SAMPLE PHOTO(S)**EFSH16112522-CG-01**

TO BE CONTINUED

SAMPLE PHOTO(S)



EFSH16112522-CG-01

TO BE CONTINUED

COMPONENT LIST

Component No.	Component	Related Sample(s)
1	Black plastic zipper teeth	A, B, C, D, E, F, G
2	Black plastic adjustable buckle	A, B, C, D, E, F, G
3	Black fabric with underlying coating	A
4	Rose red fabric with underlying coating	B
5	Orange fabric with underlying coating	C
6	Dark blue fabric with underlying coating	D
7	Sky blue fabric with underlying coating	E
8	Grey fabric with underlying coating	F
9	Wine red with underlying coating	G
10	Black fabric (handle/shoulder tape)	A, B, C, D, E, F, G
11	Black fabric (back/lining)	A, B, C, D, E, F, G

TO BE CONTINUED

TEST RESULT

Banned AZO Dyes

Test Request: Banned AZO dyes as specified in entry 43 of annex XVII of REACH Regulation (EC) No 1907/2006.

Test Method: EN 14362-1:2012
5-60 mg/kg quantitative, >60 mg/kg semi quantitative

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					3+4+5	6+7+8	10
4-Aminobiphenyl	92-67-1	mg/kg	30	5	ND	ND	ND
4,4'-Benzidine	92-87-5	mg/kg	30	5	ND	ND	ND
4-Chloro-2-methylaniline	95-69-2	mg/kg	30	5	ND	ND	ND
2-Naphthylamine	91-59-8	mg/kg	30	5	ND	ND	ND
o-Aminoazotoluene ^(Note 1)	97-56-3	mg/kg	30	5	ND	ND	ND
5-Nitro-o-toluidine ^(Note 2)	99-55-8	mg/kg	30	5	ND	ND	ND
4-Chloroaniline	106-47-8	mg/kg	30	5	ND	ND	ND
4-Methoxy-1,3-phenylenediamine	615-05-4	mg/kg	30	5	ND	ND	ND
Bis-(4-aminophenyl)methane	101-77-9	mg/kg	30	5	ND	ND	ND
3,3'-Dichlorobenzidine	91-94-1	mg/kg	30	5	ND	ND	ND
3,3'-Dimethoxybenzidine	119-90-4	mg/kg	30	5	ND	ND	ND
3,3'-Dimethylbenzidine	119-93-7	mg/kg	30	5	ND	ND	ND
3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	mg/kg	30	5	ND	ND	ND
2-Methoxy-5-methylaniline	120-71-8	mg/kg	30	5	ND	ND	ND
4,4'-Methylene bis(o-chloroaniline)	101-14-4	mg/kg	30	5	ND	ND	ND
4,4'-Oxydianiline	101-80-4	mg/kg	30	5	ND	ND	ND
4,4'-Thiodianiline	139-65-1	mg/kg	30	5	ND	ND	ND
o-Tolidine	95-53-4	mg/kg	30	5	ND	ND	ND
2,4-Diaminotoluene	95-80-7	mg/kg	30	5	ND	ND	ND
2,4,5-Trimethylaniline	137-17-7	mg/kg	30	5	ND	ND	ND
o-Anisidine	90-04-0	mg/kg	30	5	ND	ND	ND
4-Amino-azobenzene ^(Note 3)	60-09-3	mg/kg	30	5	ND	ND	ND

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

Note 1: o-Aminoazotoluene(CAS No.:97-56-3) is reduced to o-Toluidine(CAS No.:95-53-4) and quantified by this.

Note 2: 5-Nitro-o-toluidine(CAS No.:99-55-8) is reduced to 4-Methyl-m-phenylene Diamine (CAS No.:95-80-7) and quantified by this.

Note 3: 4-Amino-azobenzene(CAS No.:60-09-3) is reduced to aniline and 1,4-phenylenediamine. Need further confirmation when aniline and 1,4-phenylenediamine are detected.

TO BE CONTINUED

TEST RESULT

Banned AZO Dyes

Test Request: Banned AZO dyes as specified in entry 43 of annex XVII of REACH Regulation (EC) No 1907/2006.

Test Method: EN 14362-1:2012, EN 14362-3:2012
5-60 mg/kg quantitative, >60 mg/kg semi quantitative

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result
					11
4-Aminobiphenyl	92-67-1	mg/kg	30	5	ND
4,4'-Benzidine	92-87-5	mg/kg	30	5	ND
4-Chloro-2-methylaniline	95-69-2	mg/kg	30	5	ND
2-Naphthylamine	91-59-8	mg/kg	30	5	ND
o-Aminoazotoluene ^(Note 1)	97-56-3	mg/kg	30	5	ND
5-Nitro-o-toluidine ^(Note 2)	99-55-8	mg/kg	30	5	ND
4-Chloroaniline	106-47-8	mg/kg	30	5	ND
4-Methoxy-1,3-phenylenediamine	615-05-4	mg/kg	30	5	ND
Bis-(4-aminophenyl)methane	101-77-9	mg/kg	30	5	ND
3,3'-Dichlorobenzidine	91-94-1	mg/kg	30	5	ND
3,3'-Dimethoxybenzidine	119-90-4	mg/kg	30	5	ND
3,3'-Dimethylbenzidine	119-93-7	mg/kg	30	5	ND
3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	mg/kg	30	5	ND
2-Methoxy-5-methylaniline	120-71-8	mg/kg	30	5	ND
4,4'-Methylene bis(o-chloroaniline)	101-14-4	mg/kg	30	5	ND
4,4'-Oxydianiline	101-80-4	mg/kg	30	5	ND
4,4'-Thiodianiline	139-65-1	mg/kg	30	5	ND
o-Tolidine	95-53-4	mg/kg	30	5	ND
2,4-Diaminotoluene	95-80-7	mg/kg	30	5	ND
2,4,5-Trimethylaniline	137-17-7	mg/kg	30	5	ND
o-Anisidine	90-04-0	mg/kg	30	5	ND
4-Amino-azobenzene ^(Note 3)	60-09-3	mg/kg	30	5	ND

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

As per client's request, only the appointed materials have been tested.

Note 1: o-Aminoazotoluene(CAS No.:97-56-3) is reduced to o-Toluidine(CAS No.:95-53-4) and quantified by this.

Note 2: 5-Nitro-o-toluidine(CAS No.:99-55-8) is reduced to 4-Methyl-m-phenylene Diamine (CAS No.:95-80-7) and quantified by this.

Note 3: 4-Amino-azobenzene(CAS No.:60-09-3) is reduced to aniline and 1,4-phenylenediamine. Need further confirmation when aniline and 1,4-phenylenediamine are detected.

TO BE CONTINUED

TEST RESULT

Total Lead Content

Test Request: Total lead content as specified in entry 63 of annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Regulation (EU) No 2015/628.

Test Method: EPA 3050B:1996, EPA 3051A:2007, EPA 3052:1996
Acid digestion method was used and total lead content was determined by ICP-OES.

Tested Item(s)	Unit	Limit	MDL	Result				
				1	2	3	4+5+6	7+8+9
Total Lead	%	0.05	0.001	ND	ND	ND	ND	ND

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

As per client's request, only the appointed materials have been tested.

According to client's request, tests are combination tests. The experimental results are the total result of mixed samples.

Polycyclic Aromatic Hydrocarbons (PAHs)

Test Request: Polycyclic Aromatic Hydrocarbons (PAHs) content as specified in Regulation (EU) 2015/326 amending entry 50 of Annex XVII of REACH Regulation (EC) No 1907/2006.

Test Method: Solvent extraction and quantification by gas chromatography-mass selective detection (GC-MS) with respect to AfPS GS 2014:01 PAK (PAK=PAHs) requirement

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result
					2
For rubber or plastic will direct contact with skin and mouth.					
Benzo(a)anthracene	56-55-3	mg/kg	1	0.2	ND
Chrysene	218-01-9	mg/kg	1	0.2	ND
Benzo(b)fluoranthene	205-99-2	mg/kg	1	0.2	ND
Benzo(j)fluoranthene	205-82-3	mg/kg	1	0.2	ND
Benzo(k)fluoranthene	207-08-9	mg/kg	1	0.2	ND
Benzo(a)pyrene	50-32-8	mg/kg	1	0.2	ND
Dibenzo(a,h)anthracene	53-70-3	mg/kg	1	0.2	ND
Benzo(e)pyrene	192-97-2	mg/kg	1	0.2	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

As per client's request, only the appointed materials have been tested.

TO BE CONTINUED

TEST RESULT

Polycyclic Aromatic Hydrocarbons (PAHs)

Test Request: 18 Polycyclic Aromatic Hydrocarbons in polymers (PAHs) according to German GS Specification document: AfPS GS 2014:01 PAK (PAK=PAHs)

Test Method: Solvent extraction and quantification by gas chromatography-mass selective detection (GC-MS) with respect to AfPS GS 2014:01 PAK (PAK=PAHs) requirement

Requirement: AfPS GS 2014:01 PAK (PAK=PAHs) requirement: Limits for PAHs in Toys under Directive 2009/48/EC and Other products under ProdSG, see table 1 on next page(s):

Parameter	CAS No.	Unit	Result
			2
Benzo(a)pyrene	50-32-8	mg/kg	ND
Benzo(e)pyrene	192-97-2	mg/kg	ND
Benzo(a)anthracene	56-55-3	mg/kg	ND
Benzo(b)fluoranthene	205-99-2	mg/kg	ND
Benzo(j)fluoranthene	205-82-3	mg/kg	ND
Benzo(k)fluoranthene	207-08-9	mg/kg	ND
Chrysene	218-01-9	mg/kg	ND
Dibenzo(a,h)anthracene	53-70-3	mg/kg	ND
Benzo(ghi)perylene	191-24-2	mg/kg	ND
Indeno(1,2,3-cd)pyrene	193-39-5	mg/kg	ND
Sum of Acenaphthene, Acenaphthylene, Fluorene, Phenanthrene, Pyrene, Anthracene, Fluoranthene	-	mg/kg	ND
Naphthalene	91-20-3	mg/kg	ND
Sum 18 PAHs	-	mg/kg	ND
Summary to above mentioned requirement:	For Category 2 (Other products under ProdSG)		Pass

Remark:

mg/kg = milligram per kilogram

ND = not detected, less than 0.2 mg/kg

As per client's request, only the appointed materials have been tested.

TO BE CONTINUED

TEST RESULT

Table 1

AfPS GS 2014:01 PAK (PAK=PAHs) requirement: Limits for PAHs in Toys under Directive 2009/48/EC and Other products under ProdSG.

Parameter	Unit	Category 1 Materials indented to be put in the mouth, or materials of toys for children with foreseeable skin contact for longer than 30 seconds (long-term skin contact)	Category 2 Materials not covered by category 1, with foreseeable skin contact for longer than 30 seconds (long-term skin contact) or short-term repetitive contact with the human skin		Category 3 Materials not covered by category 1 or 2 with foreseeable skin contact up to 30 seconds (short term skin contact)	
		-	Toys under Directive 2009/48/EC	Other products under ProdSG	Toys under Directive 2009/48/EC	Other products under ProdSG
Benzo(a)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(e)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(a)anthracene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(b)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(j)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(k)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Chrysene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Dibenzo(a,h)anthracene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(ghi)perylene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Indeno(1,2,3-cd)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Acenaphthene, Acenaphthylene, Fluorene, Phenanthrene, Pyrene, Anthracene, Fluoranthene	mg/kg	<1 Sum*	<5 Sum*	<10 Sum*	<20 Sum*	<50 Sum*
Naphthalene	mg/kg	<1	<2		<10	
Sum* 18 PAHs	mg/kg	<1	<5	<10	<20	<50

* = Only those PAH components are taken into account, which have been specified in the material over the 0.2 mg/kg.

*** END OF THE REPORT ***