

**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 1 of 11

Applicant: Xindao B.V.

Address: P.O. Box 3082, 2280 GB, Rijswijk, The Netherlands

Report on the submitted sample(s) said to be:

Sample Name: Wireless charging set

Sample Model: P324.61 (wireless charging)

Sample Received Date: May 15, 2018

Testing Period: May 15, 2018 to Jun.08, 2018

**Test Requested:** Please refer to following page(s).

**Test Method:** Please refer to following page(s).

**Test Result:** Please refer to following page(s).

Tested by: Luo Xiao

Reviewed by: \_\_\_

Luoxiao Suhongliang, Leon

Test Engineer Test Team Leader

Liulinwen, Lewis

Technical Director



The results shown if this jest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by 15°C, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-cept.com.



**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 2 of 11

Test Requested: Conclusion

As specified by client, to determine the Pb, Cd, Hg, Cr<sup>6+</sup>, PBBs, PBDEs content in the submitted sample in accordance with EU RoHS Directive 2011/65/EU(RoHS) and its amendment directives on XRF and Chemical Method.

Pass

#### **Test Methods:**

A: <u>Screening by X-ray Fluorescence Spectrometry (XRF)</u>: With reference to IEC 62321-3-1:2013 Ed 1.0 Screening – Lead, mercury, cadmium, total chromium and total bromine by X-ray fluorescence spectrometry

#### B: Chemical test:

Test Item	Test Method	Measuring Instrument	MDL	
Cadmium (Cd)	IEC 62321-5:2013 Ed 1.0 Section 7	ICP-OES	2 mg/kg	
Lead (Pb)	IEC 62321-5:2013 Ed 1.0 Section 7	ICP-OES	2 mg/kg	
Mercury (Hg)	IEC 62321-4:2013 Ed 1.0 Section 7	ICP-OES	2 mg/kg	
Non-metal  Hexavalent Chromium (Cr <sup>6+</sup> )	IEC 62321-7-2:2017 Ed 1.0	UV-Vis	1 mg/kg	
Metal Hexavalent Chromium (Cr <sup>6+</sup> )	IEC 62321-7-1:2015 Ed 1.0	UV-Vis	The state of the s	
PBBs/PBDEs	IEC 62321-6:2015 Ed 1.0	GC-MS	5 mg/kg	

The results spown if this jest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ASC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-eart.com.



**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 3 of 11

### **Test Results:**

### A, EU RoHS Directive 2011/65/EU and its amendment directives on XRF

Seq.	Tooted Powt(a)		Results(mg-kg)					
No.	Tested Part(s)	Cd	Pb	Hg	Cr	Br		
1	Black plastic shell (Outer shell)	BL	BL	BL	BL	BL		
2	Ink color plastic shell (Outer shell)	BL	BL	BL	BL	BL		
3	Black rubber ring (Outer shell)	BL	BL	BL	BL	BL		
4	Coil wire sets (Coil wire)	BL	BL	BL	BL	BL		
5	Brown tape (Coil wire)	BL	BL	BL	BL	BL		
6	Coil wire core (Coil wire)	BL	BL	BL	BL	-		
7	Grey ceramic base sheet (Coil wire)	BL	BL	BL	BL	BL		
8	Chip triode	BL	BL	BL	BL	X*		
9	Chip resistor	BL	BL	BL	BL	BL		
10	Chip capacitor	BL	BL	BL	BL	BL		
11.	IC body (IC)	BL	BL	BL	BL	BL		
12	Pin (IC)	BL	BL	BL	BL	Olisuce -		
13	Tin solder	BL	BL	BL	BL	-G		
14	PCB board	BL	BL	BL	BL	X*		
15	Indicator lamp body (Indicator lamp)	BL	BL	BL	BL	X*		
16	Pin (Indicator lamp)	BL	BL	BL	BL	ation o		
17	Chip diode	BL	BL	BL	BL	X*		
18	Green PCB board	BL	BL	BL	BL	X*		
19	Tin solder	BL	BL	BL	BL	6		
20	White plastic shell (Fuse)	BL	BL	BL	BL	X*		
21	Thin film (Fuse)	BL	BL	BL	BL	BL		
22	Micro metal connector (Micro connector)	BL	BL	BL	BL	-		
23	Black plastic contact (Micro connector)	BL	BL	BL	BL	BL		
24	Contact pin (Micro connector)	BL	BL	BL	BL	-		

The results shown in this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ACC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-eatt.com.



**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 4 of 11

Seq.	The state of the s		Re	Results(mg-kg)		
No.	Tested Part(s)	Cd	Pb	Hg	Cr	Br
USB	line	K KE JIII	_ F	Kar Compliance	(8) ### ## str	ion of Global
25	Black handle (USB plug)	BL	X*	BL	BL	BL
26	Tin solder (USB plug)	BL	BL	BL	BL	-
27	White plastic plug (USB plug)	BL	BL	BL	BL	X*
28	Contact pin (USB plug)	BL	BL	BL	BL	<b>U</b> _
29	USB metal plug (USB plug)	BL	BL	BL	BL	- (117):
30	Meta contact pin (Micro plug)	BL	BL	BL	BL	impliance _
31	Tin solder (Micro plug)	BL	BL	BL	BL	<b>\</b> -C
32	Black plastic plug (Micro plug)	BL	BL	BL	BL	X*
33	Micro metal plug (Micro plug)	BL	BL	BL	X*	F Cholor
34	Black outer wire jacket (Wire)	BL	$BL^{\odot}$	BL	BL	BL
35	Green wire jacket (Wire)	BL	BL	BL	BL	BL
36	Gray wire jacket (Wire)	BL	BL	BL	BL	BL
37	Pink wire jacket (Wire)	BL	BL	BL	BL	BL
38	Wire core (Wire)	BL	BL	BL	BL	9-
39	White wire jacket (Wire)	BL	BL	BL	BL	BL

Test result on specimen No.34 was resubmitted sample on Jun.05,2018.

The results shown in this jest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by 15°C, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed in the confirmed of the confir



**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 5 of 11

anpha and	T. Timpilar	tlestation and the station		
Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x &lt;130+3σ≤OL</x 	BL≤70-3σ <x &lt;130+3σ≤OL</x 	BL≤50-3σ <x &lt;150+3σ≤OL</x 
Pb	mg/kg	BL≤700-3σ <x &lt;1300+3σ≤OL</x 	BL≤700-3σ <x &lt;1300+3σ≤OL</x 	BL≤500-3σ <x &lt;1500+3σ≤OL</x 
Нg	mg/kg	BL≤700-3σ <x &lt;1300+3σ≤OL</x 	BL≤700-3σ <x &lt;1300+3σ≤OL</x 	BL≤500-3σ <x &lt;1500+3σ≤OL</x 
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>
Br	mg/kg	BL≤300-3σ <x< td=""><td>- 1</td><td>BL≤250-3σ<x< td=""></x<></td></x<>	- 1	BL≤250-3σ <x< td=""></x<>

Note: BL= Below Limit

OL= Over limited X= Inconclusive

"-"= Not regulated

The results shown in this lest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by (SC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-cett.com.

<sup>\*=</sup> Scanning by XRF and detected by chemical method. The test results of chemical method please refer to next pages.



**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 6 of 11

#### Remark:

- Results were obtained by XRF for primary scanning, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the above warning value according to IEC 62321-3-1:2013 Ed 1.0.
- ii The XRF scanning test for RoHS elements The reading may be different to the actual content in the sample be of non-uniformity composition.

iii The maximum permissible limit is quoted from RoHS directive 2011/65/EU:

RoHS Restricted Substances	Maximum Concentration Value (mg/kg) (by weight in homogenous materials)				
Cadmium (Cd)	100				
Lead (Pb)	1000				
Mercury (Hg)	1000				
Hexavalent Chromium (Cr(VI))	1000				
Polybrominated biphenyls (PBBs)	1000				
Polybrominated diphenylethers (PBDEs)	1000				

#### Disclaimers:

This XRF Scanning report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.

The result shown in this XRF scanning report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

Test result on specimen No.37 was resubmitted sample on Jun.05,2018.

The results shown if this jest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by (SC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-eatt.com.



**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 7 of 11

#### B. The Test Results of Chemical Method:

1) The Test Results of Pb

Toot Itom(a)	Unit	Result(s)
Test Item(s)	Omt	25
Lead(Pb)	mg/kg	780

Note: N.D. = Not Detected or less than MDL

MDL = Method Detection Limit

### 2)The Test Results of metal Cr<sup>6+</sup>

	Test Item(s)	MDL	Result(s)	Limit	
ie i	Hexavalent Chromium (Cr <sup>6+</sup> )	See note	Negative	#	

#### Note

- Negative = Absence of Cr(VI) on the tested areas
- MDL = Method Detection Limit
- Boiling-water-extraction:

Number	Colorimetric result (Cr(VI) concentration)	Qualitative result
	The sample solution is <the 0,10="" cm<sup="" μg="">2 equivalent comparison standard solution</the>	The sample is negative for Cr(VI) – The Cr(VI) concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.
2	The sample solution is $\geq$ the 0,10 µg/cm <sup>2</sup> and $\leq$ the0,13 µg/cm <sup>2</sup> equivalent comparison standard solutions	The result is considered to be inconclusive – Unavoidable coating variations may influence the determination.
30	The sample solution is > the 0,13 μg/cm <sup>2</sup> equivalent comparison standard solution	The sample is positive for Cr(VI) – The Cr(VI) concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

<sup>- # =</sup>Negative indicates the absence of Cr(VI) on the tested areas concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.

Uncertainty indicates the absence of Cr(VI) on the tested areas unavoidable coating variations may influence the determination.

Positive indicates the presence of Cr(VI) on the tested areas concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).

Storage conditions and production date of the tested sample are unavailable and thus result of Cr(VI) represent status of the sample at the time of testing.

The results spown in this jest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ASC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-eart.com.



Report No.: AGC04094180504-004 Date: Jun.08, 2018 Page 8 of 11

3) The Test Results of PBBs & PBDEs

Unit: mg/kg

Ti Co Management	MDI	Result(s)			孙	
Item(s)	MDL	8	14	15	17	Limit
Polybrominated Biphenyls (PBI	Bs)					
Monobromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	
Dibromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	The same
Tribromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	opal Complia, (8)
Tetrabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	
Pentabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	
Hexabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	Total PBBs Content <1000
Heptabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	Content <1000
Octabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	Attes
Nonabromodiphenyl	5	N.D.	N.D.	N.D.	N.D.	-111
Decabromodiphenyl	5	N.D.	N.D.	N.D.	N.D.	E The
Total content	/	N.D.	N.D.	N.D.	N.D.	® Allestation of City
Polybrominated Diphenylethers	(PBDEs)			1/20		
Monobromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	-mil
Dibromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	K Compliance
Tribromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	September of Clobal (S)
Tetrabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	" GO
Pentabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	T. A. I. DDDE
Hexabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	Total PBDEs Content < 1000
Heptabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	Content <1000
Octabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	
Nonabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	
Decabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	K Manufacton (S. 48)
Total content	1	N.D.	N.D.	N.D.	N.D.	Stopped Co.
Conclusion	Tomplan	Pass	Pass	Pass	Pass	

The results shown in this jest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by SC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-cept.com. **LIGC** 



**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 9 of 11

Unit: mg/kg

Itom(a)	MDI	Result(s)			孙。	
Item(s)	MDL	18	20	27	32	Limit
Polybrominated Biphenyls (PBI	Bs)					
Monobromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	
Dibromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	刺
Tribromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	Jobal Compiler (8)
Tetrabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	
Pentabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	
Hexabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	Total PBBs Content <1000
Heptabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	Content <1000
Octabromobiphenyl	5	N.D.	N.D.	N.D.	N.D.	Atten
Nonabromodiphenyl	5	N.D.	N.D.	N.D.	N.D.	-111
Decabromodiphenyl	5	N.D.	N.D.	N.D.	N.D.	EL THE
Total content	/	N.D.	N.D.	N.D.	N.D.	® Attention of City
Polybrominated Diphenylethers	(PBDEs)			1.00		
Monobromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	-mil
Dibromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	The Compliance
Tribromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	S Global &
Tetrabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	
Pentabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	T / I PDDE
Hexabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	Total PBDEs Content < 1000
Heptabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	Content <1000
Octabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	
Nonabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	
Decabromodiphenyl ether	5	N.D.	N.D.	N.D.	N.D.	T. Harmon (S. 48)
Total content	1	N.D.	N.D.	N.D.	N.D.	Global Car
Conclusion	Tomplan	Pass	Pass	Pass	Pass	1

Note: N.D. = Not Detected or less than MDL

MDL = Method Detection Limit

The results shown in this jest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by (sc, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-cent.com.



**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 10 of 11

#### **Test Flow Chart** 1.For Pb Acid digestion with Weigh Sample Sample Preparation microwave/hotplate Filtration **DATA ICP-OES** 2.For metal Cr(VI) Boiling water extraction Adding 1,5- diphenylcarbazide for color Sample(s) Preparation development Compare with $0.1 \mu g/cm^2$ and $0.13 \mu g/cm^2$ standard UV-Vis **DATA** solution 3.For PBBs & PBDEs Cutting/Preparation Weigh Sample Sample solvent extraction Concentration/ Dilution of Extracted solution **DATA** GC-MS Filtration


### The photo of the sample




The results spown if this test report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by ASC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-eart.com.





**Report No.: AGC04094180504-004** Date: Jun.08, 2018 Page 11 of 11













AGC authenticate the photo only on original report

\*\*\* End of Report \*\*\*

The results shown if this jest report refer only to the sample(s) tested unless otherwise stated and the sample(s) are retained for 30 days only. The document is issued by (SCC, this document cannot be reproduced except in full with our prior written permission. The more details and the authenticity of the report will be confirmed at http://www.agc-eatt.com.

Add: Building 2, No.171, Meihua Road, Shangmeilin, Futian District, Shenzhen, Guangdong China

Attestation of Global Compliance Std. & Tech.