

5F Annex Dragon Pearl Plaza
2123 Pudong Avenue
Shanghai 200135 - P.R. CHINA
Tél. : +86 21 68 55 50 32
Fax : +86 21 68 55 50 33
E-mail : ctcshanghai@ctcgroupe.com

Page 1/4

Report No.: S180506281_1

16 May 2018

APPLICANT: XINDAO B. V. (C38270)

P. O. BOX 3082, 2280 GB, RIJSWIJK

Date of receipt : 10 May 2018

Testing period : 10 May 2018

: 15 May 2018

Buyer: —

Sample description: P705. 64 Bobby Weekend

Style / Article no. : P705. 64

Test(s) requested : —

Service : REGULAR

Brand / Section : —

Season : —

End use : Bobby Weekend

Factory name : —

Factory code : —

For CE Marking : Yes

Previous report : —

Product category : —

Product type : —

Test stage : FIRST TEST

Supplier name : —


Exported to : —

1. Conclusion:

	<u>Tests description</u>	<u>Conformity</u>
	EN 388	
1	Cut resistance : 2016	Level 4

Pass: requirements met Fail: requirements not met None: no requirement for this test N/A: not applicable

Approved by



Henry YAN
Laboratory Manager

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

CNAS has accredited the laboratory under the China National Accreditation Scheme (CNAS) for specific laboratory activities as listed in the CNAS directory of accredited laboratories. The results shown in this report were determined by the laboratory in accordance with its terms of accreditation.

Report No.: S180506281_1

16 May 2018

APPLICANT: XINDAO B. V. (C38270)

2. Sample(s) description assigned by laboratory:

Size	Analyzed product	Description	Sample information
	GLOVE	Palm	



180506281

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

CNAS has accredited the laboratory under the China National Accreditation Scheme (CNAS) for specific laboratory activities as listed in the CNAS directory of accredited laboratories. The results shown in this report were determined by the laboratory in accordance with its terms of accreditation.

Report No.: S180506281_1

16 May 2018

APPLICANT: XINDAO B. V. (C38270)

3. GLOVE/

Palm

	Method	Client Requirement	Unit	Result	Conformity
(+) 4.1. Cut resistance : 2016	EN 388 : 2016				
Deviation from the test method				No	
used consumables - canvas				LEM 6	
used consumables - blade				OLFA RB45	
C1				1.2	
T1				49.3	
1C1				4.3	
I1				18.9	
C2				1.1	
T2				60.0	
1C2				6.7	
I2				16.4	
C3				1.2	
T3				60.0	
1C3				5.2	
I3				19.8	
C4				1.4	
T4				60.0	
1C4				7.0	
I4				15.3	
C5				1.2	
T5				58.6	
1C5				6.8	
I5				15.7	
Mean value of test piece 1				17.2	
C1 bis				1.2	
T1 bis				32.2	
2C1bis				4.8	
I1 bis				11.7	
C2 bis				0.9	
T2 bis				35.3	
2C2bis				4.3	

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

CNAS has accredited the laboratory under the China National Accreditation Scheme (CNAS) for specific laboratory activities as listed in the CNAS directory of accredited laboratories. The results shown in this report were determined by the laboratory in accordance with its terms of accreditation.

Report No.: S180506281_1

16 May 2018

APPLICANT: XINDAO B. V. (C38270)

	Method	Client Requirement	Unit	Result	Conformity
I2 bis				14.6	
C3 bis				1.2	
T3 bis				53.2	
2C3bis				6.3	
I3 bis				15.2	
C4 bis				1.3	
T4 bis				34.3	
2C4bis				5.7	
I4 bis				10.8	
C5 bis				1.4	
T5 bis				60.0	
2C5bis				5.8	
I5 bis				17.7	
Mean value of test piece 2				14.0	
Considered value				14.0	
Performance level				4	
Observation				First sequence Cn+1 higher than 3xCn, switch to EN13997	

END OF TEST REPORT

(+)CNAS accreditation

Table of Performance Level for Glove

Test Item	Performance Level					
	0 ^{##}	1	2	3	4	5
Blade Cut Resistance (EN 388) Index (I) (minimum)	<1.2	1.2	2.5	5.0	10.0	20.0

Performance level 0 means the glove falls below the minimum performance level for the given individual hazard

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 6 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

CNAS has accredited the laboratory under the China National Accreditation Scheme (CNAS) for specific laboratory activities as listed in the CNAS directory of accredited laboratories. The results shown in this report were determined by the laboratory in accordance with its terms of accreditation.