



TEST REPORT

Test Report # 18A-003496-1
Date of Sample Received: August 23, 2018

Date of Report Issue: September 4, 2018
Pages: Page 1 of 9

CLIENT INFORMATION:

Company:
Address:



SAMPLE INFORMATION:

Product Name: ① Bottle With wireless Charging; ② Bottle with Bluetooth Earbuds
Model/style No.: ① P436.170; ② P436.120
Main Material: -
Buyer: -
Supplier: -
Country of Distribution: EU
Testing Period: 08/24/2018-08/30/2018

OVERALL RESULT:

PASS

Refer to page 2 for test result summary and appropriate notes.

HANGZHOU ASIAINSPECTION
TESTING TECHNOLOGY CO., LTD

Kevin Lee
Technical Manager

HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@asiainspection.com ♦ Tel: (86) 571 8999 7158
♦ 5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China



The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainspection Testing Technology Co., Ltd



TEST REPORT

Test Report # 18A-003496-1 Date of Report Issue: September 4, 2018
Date of Sample Received: August 23, 2018 Pages: Page 2 of 9

TEST RESULTS SUMMARY:

At the request of the client, the following tests were conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	Regulation (EC) No 1935/2004, (EU) No 10/2011 and its amendment (EU) 2016/1416- Overall migration
PASS	Regulation (EC) No 1935/2004, (EU) No 10/2011 and its amendment (EU) 2016/1416- Specific migration of heavy metals
PASS	Regulation (EC) No 1935/2004, (EU) No 10/2011 -Specific migration of Primary Aromatic Amines
PASS	Regulation (EC) No 1935/2004, (EU) No 10/2011 -Specific migration of Bisphenol A



**DETAILED RESULTS:****Regulation (EC) No 1935/2004, (EU) No 10/2011 and its amendment (EU) 2016/1416- Overall migration**

Test method: EN1186-1:2002: for selection of conditions and test methods

EN1186-9:2002: aqueous food simulants by article filling

Specimen No.		1	2	3	Maximum permissible Limit (mg/dm ²)
Simulant used	Test condition	Result (mg/dm ²)	Result (mg/dm ²)	Result (mg/dm ²)	
3% acetic acid	2 hours at 70°C	ND	ND	ND	10
Conclusion		PASS	PASS	PASS	

Note:mg/dm² = milligram per square decimeterND = Not Detected (Reporting limit = 3 mg/dm²)The overall migration value is expressed in mg/dm² applying the total contact surface of sealing article and sealed container

**DETAILED RESULTS:****Regulation (EC) No 1935/2004, (EU) No 10/2011 and its amendment (EU) 2016/1416- Specific migration of heavy metals**

Test method: Sample preparation in 3% acetic acid at 70°C for 2hours

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.		1	2	---	---	Maximum permissible Limit (mg/kg)
Test Item	Detection limit	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Barium	0.1	ND	ND	---	---	1
Cobalt	0.05	ND	ND	---	---	0.05
Copper	0.5	ND	ND	---	---	5
Iron	1.0	ND	ND	---	---	48
Lithium	0.1	ND	ND	---	---	0.6
Manganese	0.1	ND	ND	---	---	0.6
Zinc	1.0	ND	ND	---	---	5
Aluminum	0.1	ND	ND	---	---	1
Nickel	0.01	ND	ND	---	---	0.02
Conclusion		PASS	PASS	---	---	

Note:

mg/kg=milligram per kilogram

ND= Not Detected



**DETAILED RESULTS:****Regulation (EC) No 1935/2004, (EU) No 10/2011 -Specific migration of Primary Aromatic Amines**

Test Method: To refer to the EN 13130-1:2004, the analysis was performed by Gas Chromatography with Mass Spectrometry.

Specimen No.		1	2	---	---	Limit (mg/kg)
Test Item	Test condition	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Primary Aromatic Amines migration	70°C, 2h 3% Acetic acid	ND	ND	---	---	Non-detectable
Conclusion		PASS	PASS	---	---	

Note :

mg/kg = milligram per kilogram = ppm

MDL = Method Detection Limit

ND = Not Detected (Reporting Limit= 0.01mg/kg)

Primary Aromatic Amines List:

No.	Name	No.	Name
1	4-aminodiphenyl	14	p-cresidine
2	Benzidine	15	4,4'-methylene-bis-(2-chloroaniline)
3	4-chloro-o-toluidine	16	4,4'-oxydianiline
4	2-naphthylamine	17	4,4'-thiodianiline
5	o-aminoazotoluene	18	o-toluidine
6	2-amino-4-nitrotoluene	19	2,4-diaminotoluene
7	p-chloroaniline	20	2,4,5-trimethylaniline
8	2,4-diaminoanisole	21	2-methoxyaniline
9	4,4'-diaminodiphenylmethane	22	4-aminoazobenzene
10	3,3'-dichlorobenzidine	23	2,4-Xylidine
11	3,3'-dimethoxybenzidine	24	2,6-Xylidine
12	3,3'-dimethylbenzidine	25	p-Phenylenediamine
13	3,3'-dimethyl-4,4'-diaminodiphenylmethane	26	Aniline



**DETAILED RESULTS:****Regulation (EC) No 1935/2004, (EU) No 10/2011 -Specific migration of Bisphenol A**

Test method: EN 13130-1:2004 & DD CEN/TS 13130-13:2005

Specimen No.		1	---	---	---	---	Limit (mg/kg)
Test Item	Test condition	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	Result (mg/kg)	
Bisphenol A (BPA)	70°C, 2h 3% Acetic acid	ND	---	---	---	---	0.6
Conclusion		PASS	---	---	---	---	

Note :

mg/kg = milligram per kilogram = ppm

ND = Not Detected (Reporting Limit= 0.1mg/kg)





Test Report #

18A-003496-1

Pages:

Page 7 of 9

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Transparent plastic	Main body (transparent style)
2	Black plastic	Lid (transparent style)
3	Translucent soft plastic	Seal ring (transparent style)


HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@asiainspection.com ♦ Tel: (86) 571 8999 7158
♦ 5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China



*The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainspection Testing Technology Co., Ltd*



SAMPLE PHOTO:





Test Report #

18A-003496-1

Pages:

Page 9 of 9

SAMPLE PHOTO:



-End Report-



HANGZHOU ASIAINSPECTION TESTING TECHNOLOGY CO., LTD ♦ Email: Labtesting@asiainspection.com ♦ Tel: (86) 571 8999 7158
♦ 5/F A2 Building ♦ No. 1213 Huoju South Road ♦ Puyan Street ♦ Binjiang District ♦ Hangzhou ♦ China

*The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.
This test report may not be reproduced in whole or in part, without written approval of Hangzhou Asiainspection Testing Technology Co., Ltd*