

TEST REPORT

APPLICANT : Xindao B.V.

ADDRESS : P.O. Box 3082, 2280 GB, Rijswijk, The Netherlands

SAMPLE DESCRIPTION : 900D weekend/sports bag PVC free

ITEM NO. : P762.43

COUNTRY OF ORIGIN : China

COUNTRY OF DESTINATION : Europe

SAMPLE RECEIVED DATE : 30-Oct-2018

TURN AROUND TIME : 30-Oct-2018 to 07-Nov-2018

The following test item(s) was/were performed on selected sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Polycyclic Aromatic Hydrocarbons (PAHs)	German GS Specification document: AfPS GS 2014:01 PAK (PAK=PAHs)	Pass
SCCP Content	Regulation (EC) No 850/2004 (Persistent Organic Pollutants, POPs) and its amendment Regulation (EU) 2015/2030	Pass
Phthalates Content (14P)	EPA 3550C:2007, EPA 8270D:2014	Pass
Total Lead Content	REACH Annex XVII, Entry 63	Pass
Banned AZO Dyes	REACH Annex XVII, Entry 43	Pass

Eurofins (Shanghai) contact information

Customer service: ElsieWu@eurofins.com / +86 21 36202808

Sales specialist: WandyShen@eurofins.com / +86 18616155723

***** FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) *****

Signed for and on behalf of
Eurofins Product Testing Service (Shanghai) Co., Ltd



Leo Liu
Assistant Chemical Lab Manager

Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to info.sh@eurofins.com and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to china.complaint@eurofins.com and referring to this report number.

SAMPLE PHOTO



EFSH18101979-CG-01

TO BE CONTINUED

COMPONENT LIST

Component No.	Component	Quote From
1	Black coating on metal (zipper)	EFSH18101949-CG-01
2	Black fabric with transparent coating (bottom)	EFSH18101949-CG-01
3	Black fabric (body)	EFSH18101949-CG-01
4	Black plastic buckle	EFSH18101953-CG-01
5	Black soft plastic (bottom)	/
6	Black fabric tape	EFSH18101953-CG-01
7	Dark grey fabric (lining)	EFSH18101949-CG-01

TO BE CONTINUED

TEST RESULT

Polycyclic Aromatic Hydrocarbons (PAHs)

Test Request: 18 Polycyclic Aromatic Hydrocarbons in polymers (PAHs) according to German GS Specification document: AfPS GS 2014:01 PAK (PAK=PAHs)

Test Method: Solvent extraction and quantification by gas chromatography-mass selective detection (GC-MS) with respect to AfPS GS 2014:01 PAK (PAK=PAHs) requirement

Requirement: AfPS GS 2014:01 PAK (PAK=PAHs) requirement: Limits for PAHs in Toys under Directive 2009/48/EC and Other products under ProdSG, see table 1 on next page(s):

Parameter	CAS No.	Unit	Result		
			2	4	5
Benzo(a)pyrene	50-32-8	mg/kg	ND	ND	ND
Benzo(e)pyrene	192-97-2	mg/kg	ND	ND	ND
Benzo(a)anthracene	56-55-3	mg/kg	ND	ND	ND
Benzo(b)fluoranthene	205-99-2	mg/kg	ND	ND	ND
Benzo(j)fluoranthene	205-82-3	mg/kg	ND	ND	ND
Benzo(k)fluoranthene	207-08-9	mg/kg	ND	ND	ND
Chrysene	218-01-9	mg/kg	ND	ND	ND
Dibenzo(a,h)anthracene	53-70-3	mg/kg	ND	ND	ND
Benzo(ghi)perylene	191-24-2	mg/kg	ND	ND	ND
Indeno(1,2,3-cd)pyrene	193-39-5	mg/kg	ND	ND	ND
Sum of Acenaphthene, Acenaphthylene, Fluorene, Phenanthrene, Pyrene, Anthracene, Fluoranthene	-	mg/kg	ND	ND	ND
Naphthalene	91-20-3	mg/kg	ND	ND	ND
Sum 18 PAHs	-	mg/kg	ND	ND	ND
Conclusion:	For Category 2 (Other products under ProdSG)		Pass	Pass	Pass

Remark:

mg/kg = milligram per kilogram

ND = not detected, less than 0.2 mg/kg

As per client's request, only the appointed materials have been tested.

TO BE CONTINUED

TEST RESULT

Table 1

AfPS GS 2014:01 PAK (PAK=PAHs) requirement: Limits for PAHs in Toys under Directive 2009/48/EC and Other products under ProdSG.

Parameter	Unit	Category 1 Materials indented to be put in the mouth, or materials of toys intended long term skin contact (longer than 30s)	Category 2 Materials not covered by category 1, with foreseeable skin contact for longer than 30 seconds (long-term skin contact) or repeated short-term skin contact		Category 3 Materials not covered by category 1 or 2 with foreseeable skin contact up to 30 seconds (short term skin contact)	
		-	Toys under Directive 2009/48/EC	Other products under ProdSG	Toys under Directive 2009/48/EC	Other products under ProdSG
Benzo(a)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(e)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(a)anthracene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(b)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(j)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(k)fluoranthene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Chrysene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Dibenzo(a,h)anthracene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Benzo(ghi)perylene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Indeno(1,2,3-cd)pyrene	mg/kg	<0.2	<0.2	<0.5	<0.5	<1
Acenaphthene, Acenaphthylene, Fluorene, Phenanthrene, Pyrene, Anthracene, Fluoranthene	mg/kg	<1 Sum*	<5 Sum*	<10 Sum*	<20 Sum*	<50 Sum*
Naphthalene	mg/kg	<1	<2		<10	
Sum* 18 PAHs	mg/kg	<1	<5	<10	<20	<50

* = Only those PAH components are taken into account, which have been specified in the material over the 0.2 mg/kg.

TO BE CONTINUED

TEST RESULT

SCCP Content

Test Request: SCCP content as specified in Regulation (EC) No 850/2004 of the European Parliament and of the Council on persistent organic pollutants as regards Annex I and its amendment Regulation (EU) 2015/2030.

Test Method: EPA 3550C:2007, EPA 8270D:2014, solvent extraction and quantification by GC-MS.

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					2	4	5
Alkanes, C10-13, chloro (Short Chain Chlorinated Paraffins)	85535-84-8	%	0.15	0.005	ND	ND	ND

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

The production, placing on the market and use of substances or preparations containing SCCPs in concentrations lower than 1 % by weight or articles containing SCCPs in concentrations lower than 0.15 % by weight shall be allowed.

As per client's request, only the appointed materials have been tested.

TO BE CONTINUED

TEST RESULT

Phthalates Content (14P)

Test Request: Phthalates content according to client's request

Test Method: EPA 3550C:2007, EPA 8270D:2014, solvent extraction and quantification by GC-MS.

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result		
					2	4	5
Dibutylphthalate (DBP)	84-74-2	%	0.1	0.005	ND	ND	ND
Benzylbutylphthalate (BBP)	85-68-7	%	0.1	0.005	ND	ND	ND
Di-2-ethylhexylphthalate (DEHP)	117-81-7	%	0.1	0.005	ND	ND	ND
Di-n-octylphthalate (DNOP)	117-84-0	%	0.1	0.005	ND	ND	ND
Di-iso-decylphthalate (DIDP)	26761-40-0	%	0.1	0.005	ND	ND	ND
Diisononylphthalate (DINP)	28553-12-0	%	0.1	0.005	ND	ND	ND
1,2-Benzenedicarboxylic Acid, di - C6 - 8 - branched alkyl esters, C7 - 11 (DIHP)	71888-89-6	%	0.1	0.005	ND	ND	ND
1,2-Benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters (DHNUP)	68515-42-4	%	0.1	0.005	ND	ND	ND
Di-n-hexyl phthalate (DnHP)	84-75-3	%	0.1	0.005	ND	ND	ND
Diisobutyl phthalate (DIBP)	84-69-5	%	0.1	0.005	ND	ND	ND
Di-n-pentyl phthalate (DNPP)	131-18-0	%	0.1	0.005	ND	ND	ND
1,2-Benzenedicarboxylic acid, dihexyl ester, branched and linear (DIHP)	68515-50-4	%	0.1	0.005	ND	ND	ND
Bis(2-methoxyethyl) phthalate (DMEP)	117-82-8	%	0.1	0.005	ND	ND	ND
1,2-benzenedicarboxylic acid, di-C6-10-alkyl esters; 1,2-benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters with $\geq 0.3\%$ of dihexyl phthalate (EC No. 201-559-5)	68515-51-5, 68648-93-1	%	0.1	0.005	ND	ND	ND
Diisopentylphthalate (DIPP)	605-50-5	%	0.1	0.005	ND	ND	ND
1,2-Benzenedicarboxylic acid, dipentylester, branched and linear (DPP)	84777-06-0	%	0.1	0.005	ND	ND	ND
N-pentyl - isopentylphthalate (PIPP)	776297-69-9	%	0.1	0.005	ND	ND	ND

Remark:

1 mg/kg = 1 ppm = 0.0001%

MDL = method detection limit

ND = Not detected, less than MDL

As per client's request, only the appointed materials have been tested.

TO BE CONTINUED

TEST RESULT

Total Lead Content

Test Request: Total lead content as specified in entry 63 of annex XVII of REACH Regulation (EC) No 1907/2006 and its amendment Regulation (EU) No 2015/628.

Test Method: EPA 3050B:1996, EPA 3051A:2007, EPA 3052:1996
Acid digestion/ microwave digestion method was used and total lead content was determined by ICP-OES.

Tested Item(s)	Unit	Limit	MDL	Result
				1
Total Lead(Pb)	%	0.05	0.001	ND

Remark:

MDL = method detection limit

ND = Not detected, less than MDL

As per client's request, only the appointed materials have been tested.

TO BE CONTINUED

TEST RESULT

Banned AZO Dyes

Test Request: Banned AZO dyes as specified in entry 43 of annex XVII of REACH Regulation (EC) No 1907/2006.

Test Method: BS EN ISO 14362-1:2017
5-60 mg/kg quantitative, >60 mg/kg semi quantitative.

Tested Item(s)	CAS No.	Unit	Limit	MDL	Result			
					2	3	6	7
4-Aminobiphenyl	92-67-1	mg/kg	30	5	ND	ND	ND	ND
4,4'-Benzidine	92-87-5	mg/kg	30	5	ND	ND	ND	ND
4-Chloro-2-methylaniline	95-69-2	mg/kg	30	5	ND	ND	ND	ND
2-Naphthylamine	91-59-8	mg/kg	30	5	ND	ND	ND	ND
o-Aminoazotoluene (Note 1)	97-56-3	mg/kg	30	5	ND	ND	ND	ND
5-Nitro-o-toluidine (Note 2)	99-55-8	mg/kg	30	5	ND	ND	ND	ND
4-Chloroaniline	106-47-8	mg/kg	30	5	ND	ND	ND	ND
4-Methoxy-1,3-phenylenediamine	615-05-4	mg/kg	30	5	ND	ND	ND	ND
Bis-(4-aminophenyl)methane	101-77-9	mg/kg	30	5	ND	ND	ND	ND
3,3'-Dichlorobenzidine	91-94-1	mg/kg	30	5	ND	ND	ND	ND
3,3'-Dimethoxybenzidine	119-90-4	mg/kg	30	5	ND	ND	ND	ND
3,3'-Dimethylbenzidine	119-93-7	mg/kg	30	5	ND	ND	ND	ND
3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	mg/kg	30	5	ND	ND	ND	ND
2-Methoxy-5-methylaniline	120-71-8	mg/kg	30	5	ND	ND	ND	ND
4,4'-Methylene bis(o-chloroaniline)	101-14-4	mg/kg	30	5	ND	ND	ND	ND
4,4'-Oxydianiline	101-80-4	mg/kg	30	5	ND	ND	ND	ND
4,4'-Thiodianiline	139-65-1	mg/kg	30	5	ND	ND	ND	ND
o-Toluidine	95-53-4	mg/kg	30	5	ND	ND	ND	ND
2,4-Diaminotoluene	95-80-7	mg/kg	30	5	ND	ND	ND	ND
2,4,5-Trimethylaniline	137-17-7	mg/kg	30	5	ND	ND	ND	ND
o-Anisidine	90-04-0	mg/kg	30	5	ND	ND	ND	ND
4-Amino-azobenzene (Note 3)	60-09-3	mg/kg	30	5	ND	ND	ND	ND

Remark:

mg/kg = milligram per kilogram

MDL = method detection limit

ND = Not detected, less than MDL

Note 1: o-Aminoazotoluene(CAS No.:97-56-3) is reduced to o-Toluidine(CAS No.:95-53-4) and quantified by this.

Note 2: 5-Nitro-o-toluidine(CAS No.:99-55-8) is reduced to 4-Methyl-m-phenylene Diamine (CAS No.:95-80-7) and quantified by this.

Note 3: 4-Amino-azobenzene(CAS No.:60-09-3) is reduced to aniline and 1,4-phenylenediamine. Need further confirmation when aniline and 1,4-phenylenediamine are detected.

As per client's request, only the appointed materials have been tested.

END OF THE REPORT