

TEST REPORT


Customer information	Client	
	Address	
Sample information	Name of sample	Power Bank
	Test Model No.	
	Trade mark	N/A
	Manufacturer	
	Address	
Test information	Sample received	June 18, 2019
	Testing date	June 18, 2019 to July 05, 2019
	Test sort	Commission Test
	Requested/item	(1) RoHS directive 2011/65/EU (2) DIBP, DEHP, BBP, DBP
	Standard/ Foundation	(1) With reference to IEC 62321-3-1:2013, scanning by XRF Spectroscopy Chemical test method: With reference to IEC 62321-5:2013, determination of Cadmium, lead by ICP With reference to IEC 62321-4:2013+AMD1:2017, determination of Mercury by ICP With reference to IEC 62321:2008&IEC 62321-7-1:2015, determination of Hexavalent Chromium by Colorimetric method. With reference to IEC 62321-6:2015 determination of PBBs and PBDEs by GC-MS (2) With reference to EPA 3550C:2007&EPA 8270D:2007, and analysis was performed by GC-MS.
	Conclusion	(1) The tested sample complied with RoHS directive (2011/65/EU). (2) The tested part of submitted sample complied with directive (EU)2015/863
Remark	----	

Tested By:



Date: 2019/07/05

Checked By:



Date: 2019/07/05

Approved By:



Date: 2019/07/05

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline: 400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 http://www.sit-cert.com

Test result: 1. Structural parts

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
1	Gray plastic shell	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
2	Silver metal screw	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
3	Gray sponge double-sided adhesive	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
4	White colloid	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
5	Gray colloid	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
6	Black plastic frame	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
7	Black plastic key	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
8	Gray magnetic core	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
9	Yellow plastic adhesive tape	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
10	Black plastic wire skin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
11	Silver wire core	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
12	Solder	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
13	Silver metal sheet	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
14	Red plastic wire skin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
15	White cotton line cover	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
16	Copper wire core	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
17	Solder	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
18	Black IC	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
19	Yellow capacitor	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
20	Black triode	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
21	Silver metal shell	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
22	Blue plastic socket	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
23	Silver metal pin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
24	Black resistor	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
25	Black IC	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
26	Gray magnetic core	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
27	Red capacitor	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
28	Silver metal pin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
29	Black IC body	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
30	White paper	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
31	Black rubber pad	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
32	Black plastic skin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
33	Silver metal shell	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
34	Black rubber plug	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
35	Yellow paper	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
36	Gray metal foil	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
37	Silver metal pin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
38	Yellow LED	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
39	Black plastic key	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
40	Silver metal shell	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
41	White plastic base	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
42	Silver metal elastic sheet	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
43	Silver metal pin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
44	Gray magnetic core	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
45	Copper wire core	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
46	Silver metal shell	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
47	Gray plastic socket	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
48	Silver metal pin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 http://www.sit-cert.com

No.	COMPONENTS	Item	Results of EDXRF (P/F/D)	Results of Testing (mg/kg)	Chemical testing limit (mg/kg)	Conclusion (P/F)
49	Silver metal shell	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
50	Gray plastic socket	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P
51	Silver metal pin	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	/	/	<1000	/
		PBDEs	/	/	<1000	/
52	PCB	Cd	P	/	<100	P
		Cr(VI)	P	/	<1000	P
		Hg	P	/	<1000	P
		Pb	P	/	<1000	P
		PBBs	P	/	<1000	P
		PBDEs	P	/	<1000	P

Remark:

- 1 It is the result on total Br while test PBBs and PBDEs by EDXRF. It is the result on total Cr while test Hexavalent Chromium by EDXRF.
- 2 Results are obtained by EDXRF for primary screening, and chemical testing by ICP (for Cd, Pb, Hg),UV-VIS (Cr(VI)) and GCMS (for PBBs, PBDEs) is recommended to be performed, if the concentration exceeds the below warning value With reference to IEC 62321:2008 (unit:mg/kg)
- 3.

Element	Polymer	Metal	Composite Materials
Cd	$P \leq 70-3\sigma < D < 130+3\sigma \leq F$	$P \leq 70-3\sigma < D < 130+3\sigma \leq F$	$P \leq 50-3\sigma < D < 150+3\sigma \leq F$
Pb	$P \leq 700-3\sigma < D < 1300+3\sigma \leq F$	$P \leq 700-3\sigma < D < 1300+3\sigma \leq F$	$P \leq 500-3\sigma < D < 1500+3\sigma \leq F$
Hg	$P \leq 700-3\sigma < D < 1300+3\sigma \leq F$	$P \leq 700-3\sigma < D < 1300+3\sigma \leq F$	$P \leq 500-3\sigma < D < 1500+3\sigma \leq F$
Br	$P \leq 300-3\sigma < D$	----	$P \leq 250-3\sigma < D$
Cr	$P \leq 700-3\sigma < D$	$P \leq 700-3\sigma < D$	$P \leq 500-3\sigma < D$

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>

P = PASS; F = FAIL; D = DETECTED;

4. mg/kg = ppm; N.D. = NOT DETECTED (<MDL) Pb, Cd, Hg, Cr(VI): 2mg/kg; PBBs, PBDEs: 5mg/kg

5. With reference to IEC 62321:-7-1:2015, result on Cr (VI) for metal sample is shown as Positive/Negative.

Positive = Presence of Cr(VI) coating, Negative = Absence of Cr(VI) coating

6 *According to Annex III of European Council Directive 2011/65/EU, Lead in copper alloy containing up to 4% lead by weight.

7 **According to Annex III of European Council Directive 2011/65/EU, Lead in steel alloy containing up to 0.35% lead by weight.

8 #According to Annex III of European Council Directive 2011/65/EU, Cadmium and its compounds in electrical contacts is exempted.

(3) DEHP, BBP, DBP, DIBP

ITEM \ SAMPLE No.	SAMPLE CONCENTRATION (mg/kg)						MDL (mg/kg)	REQUIRED LIMIT (mg/kg)
	1	3	4	5	6	7		
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Diisobutyl phthalate (DIBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000

ITEM \ SAMPLE No.	SAMPLE CONCENTRATION (mg/kg)						MDL (mg/kg)	REQUIRED LIMIT (mg/kg)
	8	9	10	14	15	18		
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Diisobutyl phthalate (DIBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000

ITEM \ SAMPLE No.	SAMPLE CONCENTRATION (mg/kg)						MDL (mg/kg)	REQUIRED LIMIT (mg/kg)
	19	20	22	24	25	26		
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Diisobutyl phthalate (DIBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000

ITEM \ SAMPLE No.	SAMPLE CONCENTRATION (mg/kg)							MDL (mg/kg)	REQUIRED LIMIT (mg/kg)
	27	29	30	31	32	34	35		
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Diisobutyl phthalate (DIBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000

ITEM \ SAMPLE No.	SAMPLE CONCENTRATION (mg/kg)							MDL (mg/kg)	REQUIRED LIMIT (mg/kg)
	38	39	41	44	47	50	52		
Di-2-ethylhexyl phthalate (DEHP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Dibutyl phthalate (DBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Benzylbutyl phthalate (BBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000
Diisobutyl phthalate (DIBP)	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	30	1000

Note: MDL = Method Detection Limit, N.D.=not detected (<Method Detection Limit).

Sample photo

Appearance photograph of EUT



Appearance photograph of EUT




SHENZHEN SIT TESTING TECHNOLOGY CO LTD.


Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
 Hotline: 400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>

Sample photo

Appearance photograph of EUT



Appearance photograph of EUT




SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
 Hotline: 400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>

Sample photo

Appearance photograph of EUT



List of apparatus

No.	Name	Model	Calibration Valid Date	USE(✓)
1	ICP-OES	VISTA-MPX	2019/12/28	✓
2	GC-MS	5975i	2019/12/16	✓
3	UV-Vis	Lambda 25	2019/12/16	✓
4	XRF	EDX3000B	2019/12/22	✓

***** END OF REPORT *****

SHENZHEN SIT TESTING TECHNOLOGY CO LTD.

Room 401, A2 Building, The 2nd Industrial Zone of ZhuAo, GuShu Village, XiXiang Town, BaoAn District, ShenZhen
 Hotline:400-6633-940 Tel: +86-755-29173399 FAX: +86-755-29179933 <http://www.sit-cert.com>