



Technical Report: (6611)293-1065
Date Received: OCT.21, 2011
Mod. Date: /

OCT.27, 2011
Page 1 of 5

SALEEM
XINDAO (SHANGHAI) CO., LTD
15TH FLOOR, LZT TOWER, NO. 4711 JIAO TONG ROAD

Sample Description:	P459.610 TARTAN PICNIC BLANKET		
Manufacturer:	/	PO No.:	/
Buyer:	/	Style:	/
Country of Origin:	/	Country of	EU
		Destination:	
Color:	/	SKU:	/
Protocol No.:	/	Previous Report No.:	/

EXECUTIVE SUMMARY:

TEST REQUESTED	CONCLUSION	Remark
1) Free and Hydrolyzed Formaldehyde in Textiles	PASS	See test result on page 3
2) Total Cadmium Content	PASS	See test result on page 3
3) Azo Dyes Content (Analysis of Amines in Dyestuff)	PASS	See test result on page 4

SHA/JST/FF/EU



XINDAO (SHANGHAI) CO., LTD
Technical Report: **(6611)293-1065**
OCT.27, 2011
Page 2 of 5

BVCPS Shanghai contact information for this report.

Technical Questions:

Primary Contact: Justin Jin 24166758, email: Justin.Jin@cn.bureauveritas.com
Back-Up Contact: Dirk Haueisen 24166708, email: Dirk.Haueisen@cn.bureauveritas.com

Concerns About Billing and General Inquires:

Primary Contact: Jamie Wang 24166803, E-mail: Jamie.Wang @cn.bureauveritas.com
Back-Up Contact: Connie Zhou 24166816, E-mail: Connie.Zhou @cn.bureauveritas.com

**BUREAU VERITAS
CONSUMER PRODUCTS SERVICES (SHANGHAI)**

DIRK HAUEISEN
TECHNICAL DIRECTOR HARDLINES

The Test Results are Listed As Below:

1. Free and Hydrolyzed Formaldehyde in Textiles

Parameter	Unit	Result	Client's limit
		1	
Formaldehyde	mg/kg	ND	75ppm
Conclusion	-	PASS	-

Test Item 1: Main fabric + handle fabric + connect fabric of handle

Note: mg/kg = milligram per kilogram
 ND = Not Detected
 Detection Limit (mg/kg) : Each 20

Method: ISO 14184-1: 1998

2. Total Cadmium Content

Compounds	Unit	Tested item	Maximum Allowable Limit
		1	
Cadmium (Cd)	mg/kg	ND	100
Conclusion	-	PASS	-

Test Item 1: Main fabric + handle fabric + connect fabric of handle

Note: mg/kg = milligram per kilogram
 ND = Not Detected
 Detection Limit (mg/kg) : Each 10

Method: Acid digestion method (plastic), wet digestion method with mixed acid (metal),
 and determined by Inductively Coupled Argon Plasma Spectrometer / Atomic Absorption Spectrometer.

Remark: The test item was specified by the applicant

3. Azo Dyes Content (Analysis of Amines in Dyestuff)

Parameter	CAS-No	Unit	Result	Client's Limit
			1	
o-Toluidine	95-53-4	mg/kg	ND	30
2-Methoxyaniline	90-04-0	mg/kg	ND	30
p-Chloroaniline	106-47-8	mg/kg	ND	30
p-Kresidine	120-71-8	mg/kg	ND	30
2,4,5-Trimethylaniline	137-17-7	mg/kg	ND	30
4-Chloro-o-Toluidine	95-69-2	mg/kg	ND	30
2,4-Toluylenediamine	95-80-7	mg/kg	ND	30
2,4-Diaminoanisole	615-05-4	mg/kg	ND	30
2-Naphthylamine	91-59-8	mg/kg	ND	30
2-Amino-4-nitrotoluene	99-55-8	mg/kg	ND	30
4-Aminodiphenyl	92-67-1	mg/kg	ND	30
p-Aminoazobenzene	60-09-03	mg/kg	ND*	30
4,4'-Oxydianiline	101-80-4	mg/kg	ND	30
Benzidine	92-87-5	mg/kg	ND	30
4,4'-Diaminodiphenylmethane	101-77-9	mg/kg	ND	30
o-Aminoazotoluene	97-56-3	mg/kg	ND	30
3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	mg/kg	ND	30
3,3'-Dimethylbenzidine	119-93-7	mg/kg	ND	30
4,4'-Thiodianiline	139-65-1	mg/kg	ND	30
3,3'-Dichlorobenzidine	91-94-1	mg/kg	ND	30
4,4'-Methylene-bis-(2-chloraniline)	101-14-4	mg/kg	ND	30
3,3'-Dimethoxybenzidine	119-90-4	mg/kg	ND	30
2,4 - Xylidine	95-68-1	mg/kg	ND	30
2,6 - Xylidine	87-62-7	mg/kg	ND	30
Conclusion	-	-	PASS	-

Test Item	Description	Test Method
1	Main fabric + connect fabric of handle	EN 14362-1 EN 14362-2

Note: mg/kg = milligram per kilogram
 ND = Not Detected
 Detection Limit (mg/kg) : Each 10.0

Method: EN 14362-1: 2003 incorporating Corrigendum 2005 – For textile with azo colorants accessible without extraction
 EN 14362-2: 2003 incorporating Corrigendum 2005 – For textile with azo colorants accessible by extracting the fibers

Remark : *Azo colorants that are able to form p-aminoazobenzene, generate aniline and 1,4-phenylenediamine under the condition of this method. Aniline and 1,4-phenylenediamine are not detected under the condition of this method.

EXHIBIT



END